

Bonntile Hong Kong Limited

邦盛建材香港有限公司

TECHNICAL DATA SHEET

Bonndeco HydroFlon

Modified Fluorocarbon Resin

Product Description


Using a Modified Fluorocarbon resin. It has weather resistance, anti-pollution, antiultraviolet and strong adhesion. It is a high-tech decorate coating with elegant film and delicate smooth surface built which has combinative performance of functionality and high decorative.

Features & Benefits

- Excellent water & alkali resistant
- Excellent weather and scrub resistant
- Excellent washability
- Anti-carbonation
- Extremely color consistency
- Algae and fungus resistant
- Extremely dirt resistant

Typical Painting System			
Preparation	System		
Surface should be smooth, clean and dust free.	Sealer	Bonndeco Ultra Sealer -1008(1 coat)	
	Intermediate coat	Bonndeco Water Base intermediate coat- G203 (1 coat)	
	Topcoat	Bonndeco HydroFlon-GL9901 (1 coat)	

Properties		
Condition in container	There shall be no lumps, no separation and no coagulation of the ingredients	
Low temperature stability @-5°C	Unchanged	
Coating appearance	Normal	
Drying time @20°C	<2 hours	
Color contrast (White and light)	≥ 0.96	
Adhesion Test	≤ 1 Level	
Alkali resistance (168 hours)	Unchanged	
Acid Rain Resistance (48 hours)	Unchanged	
Water resistance (168 hours)	Unchanged	
Washability (3,000 times)	No damaged	
Dirt resistance (%)	10 %	
Weatherability (1,700 hours)	Appearance: No peel off, No crack Chalking 0 Discoloration 1	



Tel: 852-2341 9201 Fax: 852-2763 5348



Application Surfaces

It is suitable for the application to exterior /interior surfaces of the following substrates:-

- Precast Concrete,
- Poured in Place Concrete,
- Plaster (Mortar), Stucco, GRC
- · Tile Filler, Existing paint film

Application Locations

It is suitable for the application to exterior/interior surface of the following locations:-

- Walls and columns
- Ceilings and beams
- · Fence walls, Roof parapets
- Bends, etc.

Application

Roller, Spray, Brush

Glossiness

Matt, Semi-glossy, Glossy

Color

Standard color chart from Bonndeco tailor made color

Package available

20kg/can

Thinning ratio

5 ~ 10%

Drying time

At least two (2) eight (8) hours, depending on the weather condition at the time of application.

Theoretical spreading ratio

Approximately 140-160m2/coat/can

Remarks:-

Issued July 2019 FC-10

The recommended coverage rates, including those of normal wastage, are for reference only. Actual coverage may vary depending on the working condition of the site, the degree of evenness and smoothness of the substrate surface, and the pattern of the texture sample as selected and approved by the architector client.

^{2.} We reserve the right to change or adjust the composition of material used in the specification of our products due to our constant research and development to improve of the quality of our products.



Bonntile Hong Kong Limited

邦盛建材香港有限公司

加量性的首他有限公

TECHNICAL DATA SHEET

Bonndeco HydroFlon

Modified Fluorocarbon Resin

Instruction for use

Surface Treatment & Condition Requirement New Surface

- Substrates must be properly cured before applications.
- Application surface must be smooth and free of voids or sharp projections.
- c. Any application surface such as precast concrete, with excess pinholes, honeycomb, cracks, uneven or porous condition, should be filled up prior to the application.
- Any application surface, with laitance, efflorescence, dust, rust, oil grease, curing agent etc. must be removed completely by brushing, sanding or other effective means.
- e. Recheck surface after repair to assure satisfactory condition prior to Bonndeco application.

Old Surface

- All loose coating on the application surface should be removed by wire brushing, Sanding or other effective means.
- Any laitance, efflorescence, dust, rust or oil grease must be removed completely by brushing, sanding or other effective means.
- All defective areas, hollow plasters and spoiling concrete must be hacked off.
- Defective wall surfaces must be repaired by filling cracks or re-plastering of hacked off portions.
- e. To paint areas must be cleansed by high pressure water jet at 1,500 psi and all surfaces should be of the sound, clean, dry and sufficiently smooth that accepted as an appropriate substrate for the application of Bonndeco Products.

Fungus

Remove by high-pressure water jet wash and treated with anti-fungus solutions. Allowed to dry before painting.

Grease

Clean Off with mild detergent and a little solvent. Wash thoroughly to remove all trace.

Application Procedure

 Shake and stir thoroughly to get a complete dispersion of pigment.

Tel: 852-2341 9201

Fax: 852-2763 5348

Use standard practice, either by rolling, brush or spraying, to ensure conformance to the specification requirement.

Flat C2, 11/F., Hang Fung Industrial Building Phase 2,

2G Hok Yuen Street, Hung Hom, Kowloon

- Drying time may take at least two (2) or eight (8)hours at 10°C-20°C
- Workers, applying in confined areas, are required to wear protection masks and exhaust ventilation should be properly supplied to the confined area.

Precautions in use Handling and storage

- Do not use near flames
- All workplaces to always have specific ventilating equipment in operation.
- Particular precautions to be taken for good ventilation during application and while drying, and precautions taken to avoid any inhaling of fumes.
- During handling, precautions to be taken to avoid any skin contact and as necessary, gas mask against organic gas or fresh air supplying masks to be worn and also use head towels, wear protective eyeglasses, long sleeved protective gowns, neck protecting towels, protective gloves, etc.
- When coat is spilled, wipe with waste cloths to be kept stored in water filled containers.
- Until final disposal, all waste cloths that have been exposed to coat, hardeners or thinners, and leftover coat, spray dust, etc. for disposal shall be kept doused in water filled containers.
- After handling or application, hands to be thoroughly washed and extensive gargling is advised.
- The handles on the upper part of the tin containers are solely for carrying the tins. Please do not use ropes and hooks on the handles for hanging the tins.
- During storage, containers are to be tightly sealed and stored out of any direct sunlight or any exposure to rain, in a cool, well ventilated area.
- Please store away from any foreign instruction by third parties and out of the reach of children.

Cleaning Up

Clean all equipment with clean water immediately after use.

Remarks:-

Issued July 2019 FC-10

[.] The recommended coverage rates, including those of normal wastage, are for reference only. Actual coverage may vary depending on the working condition of the site, the degree of evenness and smoothness of the substrate surface, and the pattern of the texture sample as selected and approved by the architect or client.

^{2.} We reserve the right to change or adjust the composition of material used in the specification of our products due to our constant research and development to improve of the quality of our products.



Bonntile Hong Kong Limited

邦盛建材香港有限公司

2, 2G Hok Yuen Street, Hung Hom, Kowloon Tel: 852-2341 9201

Flat C2, 11/F., Hang Fung Industrial Building Phase

Tel: 852-2341 9201 Fax: 852-2763 5348

TECHNICAL DATA SHEET

Bonndeco HydroFlon

Modified Fluorocarbon Resin

Job Reference

Project	Main Contractor /Owner	Year
澳門板樟堂16A-16E及大堂巷-5號交界地段		2018-2019
逸瓏海滙 Park Mediterrancean, 9 Hong Tsuen Road, Sai Kung	Sino Land Company Ltd	2017-2018
明愛專上學院 Caritas Institute of Higher Education Tseung Kwan O Town Lot 97, Area 73B, Tsueng Kwan O	Caritas Institute of Higher Education	2017-2018
澳門美高梅 MGM Cotai, Avenida Dr. Sun Yat Sen, NAPE, Macau	MGM Holdings Ltd	2016-2017
招商局物流中心 China Merchants Logistics Centre, 38 Tsing Yi Hong Wan Road, Tsing Yi	China Merchants Ltd	2016-2017
SS D828 Construction of Public Toilet at Sheung Shui Garden No.1	ASD	2016-2017
東華三院馬錦燦紀念小學 TWGHs Ma Kam Chan Memorial Primary, 2 Ching Shing Road, Sheung Shui, N.T.	Tung Wah Group of Hospitals	2016-2017
亞洲貨債物流中心 Renovation Works for G/F Lift Lobbies, Drop Off Area & Public Area at G/F of Centre A&B of ATL Logistics Centre, Berth 3, Kwai Chung	ATL Logistics Centre Hong Kong Ltd	2015-2106
香港專業教育學院 IVE Chai Wan, 30 Shing Tai Road, Chai Wan, Hong Kong	Vocational Training Council	2015-2016
香港理工大學 Block Z, The Hong Kong Polytechnic University, Hung Hom	The Hong Kong Polytechnic University	2013-2014

Remarks:

Issued July 2019 FC-JR

^{1.} The recommended coverage rates, including those of normal wastage, are for reference only. Actual coverage may vary depending on the working condition of the site, the degree of evenness and smoothness of the substrate surface, and the pattern of the texture sample as selected and approved by the architect or client.

^{2.} We reserve the right to change or adjust the composition of material used in the specification of our products due to our constant research and development to improve of the quality of our products.